

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
20 December 2001 (20.12.2001)

PCT

(10) International Publication Number  
**WO 01/96454 A1**

(51) International Patent Classification<sup>7</sup>: **C08K 3/08**,  
3/10, H01J 1/62, H01L 33/00

(21) International Application Number: **PCT/US01/18867**

(22) International Filing Date: **12 June 2001 (12.06.2001)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:  
**60/211,108** **12 June 2000 (12.06.2000)** **US**

(71) Applicant (for all designated States except US): **MAX-DEM INCORPORATED [US/US]**; 140 East Arrow Highway, San Dimas, CA 91773 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **MARROCCO, Matthew, L., III [US/US]**; 9892-1 Arrow Route, Rancho Cucamonga, CA 91730 (US). **MOTAMEDI, Farshad, J. [US/US]**; 1381 North Birchnell Avenue, San Dimas, CA 91773 (US).

(74) Agent: **CHRISTIE, William, P.**; Christie, Parker & Hale, LLP, P.O. Box 7068, Pasadena, CA 91109-7068 (US).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.


(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **POLYMER MATRIX ELECTROLUMINESCENT MATERIALS AND DEVICES**



(57) Abstract: Photoluminescent and electroluminescent compositions are provided which comprise a matrix comprising aromatic repeat units and a luminescent metal ion or luminescent metal ion complex. Methods for producing such compositions, and the electroluminescent devices (10) formed therefrom, are disclosed.

WO 01/96454 A1

## POLYMER MATRIX ELECTROLUMINESCENT MATERIALS AND DEVICES

## FIELD OF THE INVENTION

This invention relates to photoluminescent and electroluminescent compositions comprising a matrix comprising aromatic repeat units and a luminescent metal ion or a luminescent metal ion complex. The invention also relates to method for making such compositions and electroluminescent devices using such compositions.

## BACKGROUND OF THE INVENTION

Many types of luminescent devices exist, including a number of all solid state devices. Solid state devices are preferable over incandescent or fluorescent bulbs in that they are lighter; more compact, can be made smaller, and can have higher efficiency. Examples of solid state luminescent devices are light emitting diodes (LEDs), such as gallium arsenide or silicon carbide LEDs, organic light emitting diodes (OLEDs), such as OLED displays being marketed by Uniax Corporation and CDT Ltd., and doped zinc sulfide devices that have been marketed for a number of years, for example by GE® as Limelite™ nightlights, and American Tack and Hardware, Co. Inc., (Monsey, NY) as Nitelite™ nightlights. Any of these devices can be fabricated into arrays to represent numbers or letters, or pictures.

Of the various luminescent devices and displays the OLEDs are the newest and least mature technology. OLEDs typically consist of a thin film structure comprising a transparent electrode, usually indium doped tin oxide (ITO) on a glass or plastic support layer, the ITO optionally coated with polyaniline or poly(ethylenedioxythiophene) (PEDOT), one or more organic containing layers, typically a hole conducting layer, for example, of a triphenylamine derivative, a luminescent layer, for example, a polyphenylenevinylene derivative or a polyfluorene derivative, an electron conducting layer, for example, an oxadiazole derivative, and a second electrode, for example, calcium, magnesium, aluminum, and the like.

The advantages of the OLED devices are, lightweight, potentially low cost (although this has yet to be demonstrated commercially), the ability to fabricate thin film, flexible structures, wide viewing angle, and high brightness. The disadvantages of OLEDs are short device lifetimes, increasing voltages when operated in a constant current mode, and broad spectral widths. The efficiency of OLEDs is limited by the nature of the excited state of organic molecules. Typically, both the singlet and triplet excited states are populated during the operation of an OLED. Unfortunately, only decay from the singlet state produces useful light. Decay

1 from the triplet state to a singlet ground state is spin forbidden and therefore slow, giving non-radiative processes more time to take place. Because the triplet state is three-fold degenerate and the singlet state is not degenerate; three quarters of the excited electrons enter the triplet state and produce little or no light.

5 An additional disadvantage of OLEDs is the relatively short lifetime of the excited state of organic molecules. In a display application each pixel is scanned 10 to 100 times every second, typically 60 times every second. It is desirable for the light from the pixel to decay on about the same time scale. If the pixel decays too slowly each subsequent image will be scanned over the not yet faded previous image, and the image will blur. If the pixel decays too quickly, there will be a noticeable flicker.

10 There is a need for a solid state device that is not limited by the short lifetimes of OLEDs. The short life of OLEDs is suspected to arise from the decomposition or alteration of the organic layers during operation.

15 There is also a need for electroluminescent devices that have stable I-V characteristics making the associated electronics simpler.



There is also a need for electroluminescent devices with pure color characteristics that are more amenable to color displays. For color television, monitors, and the like, red, blue, and green devices with exacting color are required.











20 There is also a need for electroluminescent devices with higher efficiency, not limited by decay from non-luminescent triplet states.

There is also a need for electroluminescent devices with phosphorescent decay times in the appropriate range for scanned displays and passive displays.

## SUMMARY OF THE INVENTION

25 In one aspect, the present invention is directed to a polymer composition comprising repeat units selected from the group consisting of:





1 where R is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, arylerster, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy, any two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, r is 0-7, A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-,  
5 -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, Cl, Br, I, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, and E is selected from the group consisting of O, NH, and S,  
and one or more fluorescent metal ions.

10 In another aspect, the invention is directed to an electroluminescent device comprising the composition set forth above. In one embodiment, the electroluminescent device comprises a first electrode, one or more charge transport layers, an electroluminescent layer comprising the composition set forth above and a second electrode.

#### 15 BRIEF DESCRIPTION OF THE DRAWINGS

These and other features, aspects, and advantages of the present invention will be more fully understood when considered with respect to the following detailed description, appended claims, and accompanying drawings, wherein:

20 FIG. 1 is a semi-schematic side view of one embodiment of an electroluminescent device provided in accordance with practice of the present invention;

FIG. 2 is a semi-schematic exploded view of the electroluminescent device of FIG. 1;

25 FIG. 3 shows an array of electroluminescent devices extending in two dimensions provided in accordance with practice of the present invention;

FIG. 4 is a semi-schematic side view of another embodiment of an electroluminescent device provided in accordance with practice of the present invention which comprises an electron transfer layer but no hole transfer layer; and

30 FIG. 5 is a semi-schematic side view of an electroluminescent device provided in accordance with practice of the present invention having a graded electroluminescent layer.

#### DETAILED DESCRIPTION

35 In order to overcome the deficiencies of previous luminescent devices it would be desirable to have a device with higher efficiency than current OLEDs, and with longer lifetimes. It would also be desirable to have a device that operated at low voltage, preferably less than 20 volts, more preferably less than 15 volts, even more

1 preferably less than 10 volts, and most preferably less than 5 volts DC. It would also  
be desirable to have a device with good color quality, and appropriate  
phosphorescent decay time for displays.

5 We have found that many of the disadvantages of OLEDs may be overcome by  
use of a combination of a fluorescent metal ion and an organic matrix designed to  
collect and deposit energy into the fluorescent metal ion, as the luminescent layer(s)  
in an electroluminescent device. The matrix typically comprises a polymer, but may  
be an oligomer, or discrete molecules. The matrix will accept electrons and/or holes  
10 from the electrodes and transport them toward the center of the device where they  
recombine to produce an excited electronic state in the matrix. Materials that  
fluoresce well tend to also electroluminesce well, and are thus good candidates for  
the matrix of the present invention. The band gap of the matrix (or in other terms  
the HOMO-LUMO difference) will determine the energy of the excited state, and  
15 how much energy is available to excite the luminescent metal. A polymer matrix  
that luminesces in the red will generally not be able to transfer energy to a metal  
that luminesces blue, except in the unusual case of a two photon or higher order  
process. Thus it is desirable to choose a polymer matrix that luminesces blue, indigo,  
violet, or ultraviolet, i.e., the high energy part of the spectrum, so that transfer to  
metals that luminesce blue, green, or red is possible.

20 The fluorescent spectrum of organic polymers, oligomers, and discrete organic  
molecules are typically very broad, often 50 or 100 nm wide. The absorption and  
emission bands of lanthanide metals are very narrow, typically 5 to 20 nm, because  
the bands result from transitions between f orbitals which are "buried" within outer  
filled d and s orbitals. Since they are screened by the outer d and s orbitals they are  
less effected by external electric fields and transitions within the f manifold are not  
25 broadened. The narrow bands provide very pure colors, a desirable feature for  
display fluorophors.

30 Lanthanide metals have been used as cathodoluminescent materials for many  
years in color television picture tubes, commonly called cathode ray tubes (CRTs). It  
is well known that certain lanthanide metals have fluorescent bands very near the  
ideal color coordinates for red, blue and green, in CRTs. By using a polymer matrix  
(with its broad spectrum) to excite a lanthanide metal (with its narrow spectrum,  
and good color coordinates) a much better color rendition is achieved. The  
lanthanides are yttrium, lanthanum, cerium, praseodymium, neodymium,  
promethium, samarium, europium, gadolinium, terbium, dysprosium, holmium,  
35 erbium, thulium, ytterbium, and lutetium.

1 Lanthanide metals, and other luminescent metals, have excited state lifetimes that are closer to the lifetime needed for displays than are the lifetimes of organic materials.

5 The excited state of a lanthanide ion produces much more light (about four times more) than an excited organic compound. Also, the luminescent metal ion or complexes can accept energy from both singlet and triplet states of organic molecules. In this way, the excited energy in the organic singlet state that was otherwise destined to be lost to non-radiative transitions is transferred to a metal, which then radiates.

10 Metal ions are much less subject to bleaching or chemical reactions that destroy the fluorophor than organic species. The term fluorophor is used here to mean the chemical system that absorbs energy and re-emits it, typically the emitted energy is light of lower energy than the absorbed energy. The chemical system may be an atom, an ion, a molecule, a metal complex, an oligomer, a polymer, or two or more atoms, ions, or molecules in close proximity, capable of exchanging energy. 15 Fluorophors may be, but are not limited to being, photoluminescent, fluorescent, phosphorescent, cathodoluminescent, or electroluminescent. Although the devices of the instant invention are still partly organic, the metal ions exert a protective effect by removing energy from the organic excited state. The devices of the present invention are thus expected to have longer lifetimes than all organic devices.

20 In the practice of the present invention, a luminescent or fluorescent metal ion or complex, preferably a lanthanide metal ion or complex, is embedded within a fluorescent organic matrix, producing a system wherein the organic matrix may be elevated to an excited state, which then transfers its energy to the metal ion or complex which then emits light. The energy transfer between organic matrix and metal may be enhanced by providing coordination sites for the metal on the organic 25 matrix. The energy transfer may also be enhanced by providing the metal with polarizable ligands.

30 The luminescent metal ion may be any metal ion or metal complex that luminesces, including, but not limited to, transition metal ions such as manganese, silver, ruthenium, iridium, and platinum, lanthanide ions, and complexes thereof. Lanthanide ions are preferred because of their narrow spectral line widths.

35 The electroluminescent (EL) compositions and EL devices of the present invention will have very narrow emission lines because the emission is primarily from a lanthanide metal ion. As noted above, lanthanide metal ions have narrow emission bands, typically 5 to 20 nm in width (full width at half maximum, FWHM). The FWHM of the electroluminescent compositions and devices of the present invention will be less than about 50 nm, preferably less than about 20 nm, more

1 preferably less than about 10 nm, even more preferably less than about 8 nm, yet  
more preferably less than about 5 nm, even yet more preferably less than about 4  
nm, and most preferably less than 3 nm.

5 The luminescent metal ion may be coordinated or complexed to a ligand, or  
may be complexed or coordinated to a polymer. One or more counter ions may also  
be present, and these may or may not coordinate to the metal. The luminescent  
metal ions may form clusters or may be part of a cluster of metals. Ligands and  
counter ions may also coordinate two or more luminescent metals, in a bridging  
fashion.

10 The luminescent metal ions may be present as part of an inorganic solid. For  
example, an inorganic powder, comprising a luminescent metal ion may be mixed  
with a luminescent polymer. The inorganic powder is preferably 400 mesh (average  
particle size less than about 38 microns), or finer, more preferably less than about 20  
microns, even more preferably less than about 5 microns, and most preferably less  
15 than about 3 microns. The inorganic powder may be a nanosized powder with  
average physical dimensions in the 1 to 1000 nanometer range, preferably less than  
about 500 nanometers, and more preferably less than about 100 nanometers.  
Nanometer sized particles have very high surface to volume ratios and a high  
fraction of the metal ions are at the surface of the particle or within several  
20 angstroms (several tens of nanometers) of the surface, making energy transfer from  
a polymer in which the powder is embedded possible. Nanosized particles less than  
about 300 nm do not scatter visible light. In the practice of the present invention,  
the light emitting films may be less than 1000 nm and, if particles are to be used,  
the particles must be smaller than the film thickness. The inorganic solid may be a  
semiconductor. Non-limiting examples of semiconductors are gallium nitride, tin  
25 oxide, zinc oxide, zinc sulfide, cadmium sulfide, cadmium selenide, lead oxide, and  
the like. Semiconductors comprising elements of groups II and VI (II-VI  
semiconductors) can often be prepared by wet chemical methods and are therefore  
preferred.

30 Merely mixing a fluorescent polymer with a fluorescent metal ion or complex  
does not guarantee that energy can be transferred from the polymer to the metal.  
The excited state of the polymer must be at a higher energy level than the excited  
state of the metal, otherwise little or no energy will be transferred. Additionally, we  
have found that the probability of energy transfer can be increased by providing a  
polymer having functional groups, either side groups, or main chain groups, or end  
35 groups, that bind or coordinate to the luminescent metal ion, or metal complex. Any  
functional group that coordinates to a metal may be used. It will be understood by  
one skilled in the art how to determine if a functional group is coordinated, for



1 example, by observation of spectral shifts of the functional group in the IR, visible,  
or NMR spectra. Functional groups may be monodentate, or chelating multidentate,  
or macrocyclic. Functional groups that may be used include but are not limited to  
amines, amides, alcohols, alpha diketones, alpha ketoalcohols, beta diketones, beta  
5 ketoalcohols, beta ketoacids, bipyridines, biquinolines, borates, carboxylic acids,  
catecols, diols, hydroxyquinolines, phenanthrolenes, phenols, phosphates,  
polyamines, polyethers, pyridines, quinolines, salicylates, sulfates, thioethers, thiols,  
thiophenes, and the like. Functional groups may lose one or more protons upon  
coordination to the luminescent metal ion.


10 The functional groups on the polymer may replace all or some of the ligands  
on the fluorescent metal. That is, the metal may have additional ligands other than  
the polymer functional groups, including coordinated solvent, and coordinated  
counter ions.

We have also found that the luminescent metal ion complex may be chosen to  
enhance energy transfer from polymer to metal. Even if the metal is not bound  
15 directly to the polymer by a covalent or coordinate bond, energy transfer may be  
enhanced by choosing a ligand that interacts with the polymer, e.g., by van der  
Waals, hydrogen bonds, dipole-dipole, dipole-induced dipole, or other non-covalent  
interaction. Energy transfer may be enhanced by use of a ligand bearing polarizable  
groups, for example, aromatic groups and especially multiple or fused ring aromatic  
20 groups such as biphenyl, triphenyl, quaterphenyl, naphthyl, anthracenyl,  
phenanthrenyl, pyridyl, quinoliny, phenanthrolinyl, benzoxazolyl, and the like. A  
polarizable ligand in general has electrons that can respond to an electric or  
electromagnetic field. For the purposes of the present invention, a polarizable  
ligand will have at least one double bond; preferably, a carbon-carbon double bond.  
25 More preferably, the polarizable ligand will have two or more double bonds; even  
more preferably, three or more double bonds; yet more preferably, four or more  
double bonds; even yet more preferably, five or more double bonds; and most  
preferably, six or more double bonds. It is further preferable that some or all of the  
double bonds be conjugated with one another. The double bonds may be part of an  
30 aromatic or heteroaromatic ring, such as a benzene, pyridine, or quinoline ring. The  
aromatic ring may be terminal (eg., phenyl) or internal (e.g., phenylene). For the  
purposes of the present invention, conjugated ligands are polarizable ligands.


Non-limiting examples of polarizable ligands include benzoylacetone,  
dibenzoylmethane, benzoin, phenanthroline, phenylphenanthroline, bipyridine,  
35 phenylbipyridine, diphenylbipyridine,  $\text{Ar}(\text{CO})(\text{CHOH})\text{Ar}'$ ,  $\text{Ar}(\text{CO})\text{CH}_2(\text{CO})\text{Ar}'$ ,  
salicylic acid, salicylaldehyde, phenylsalicylic acid, phenylsalicylaldehyde, adenine,  
purine, 2-aminobenzophenone, 2-amino-4-chlorobenzophenone, 2-(2-

hydroxyphenyl)benzothiazole, 2-(2-hydroxyphenyl)quinoline, 1-naphthol-2-carboxaldehyde, 1,2-dihydroxybenzene, 1,2-dihydroxynaphthalene, 2,3-dihydroxynaphthylene, 1,8-dihydroxynaphthylene, 1-hydroxybenzophenone, 1-hydroxyfluorenone, 7-hydroxyinden-1-one, 7-hydroxy-3-phenylinden-1-one, salen, 8-hydroxyquinoline, 8-hydroxyquinazoline, 8-hydroxyquinoxaline, 4-hydroxybenzoxazole, 7-hydroxybenzoxazole, 4-hydroxy-2-phenyl benzoxazole, 7-hydroxy-2-phenylbenzoxazole, hypoxanthine, and the like. Aryl, Ar and Ar' are independently selected from the group consisting of phenyl, 2-biphenyl, 3-biphenyl, 4-biphenyl, 1-naphthyl, 2-naphthyl, 2-pyridyl, 3-pyridyl, 4-pyridyl, terphenyl (any isomer), quaterphenyl (any isomer), anthracenyl, phenanthrenyl, pyridyl, quinolinyl, phenanthrolinyl, benzoxazolyl, and quinazolinyl, optionally substituted with D (deuterium), F, Cl, Br, I alkyl, alkoxy, polyalkaleneoxy and fluoroalkyl. Preferably a ligand will have at least one aromatic ring, more preferably a ligand will have at least two aromatic rings, even more preferably a ligand will have at least three aromatic rings. Preferably a ligand will have a direct bond between two of the aryl groups such that they form a biaryl group, or will have two rings in a fused ring system. Biaryls and fused rings have higher polarizability than single ring systems and therefore will couple better to the polymer excited state. It is also preferable for the ligand to have a triaryl group or fused three-ring group.


Non-limiting examples of general structural formulae of polarizable ligands are shown below.




1




2



3




4





5




1







5




10



15




20





25


30



35



where R is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, aryloxy, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy (e.g. methoxyethoxyethoxy, ethoxyethoxy, and  $-(OCH_2CH_2)_xOH$   $x=1-100$ ), two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, r is 0-7, and s is 0-8. The R groups may be on any ring in a multiple ring structure. For example, in structure 12 there may be R groups on the heterocyclic ring, on the phenolic ring, or on both. An example of bridging R groups is given in structure 20 below. Structure 20 is derived from structure 8 where two of the R groups taken together are  $-CH=CH-CH=CH-$ .


20

Additional examples of polarizable ligands include  $R-C_6H_4-CO_2H$ ,  $R-C_6H_4-SO_3H$ ,  $R-C_6H_4-PO_3H_2$ , substituted nicotinic acids  $R-C_5H_3N-CO_2H$ , substituted salicylic acids, and the like.


It will be apparent to one skilled in the art that the polarizable ligands could be used as functional groups if they are covalently attached to a polymer chain. For example, any of the R groups in the structures could represent a polymer chain. A polarizable ligand may also form part of the backbone of a polymer chain, for example, being attached through R groups (in the cases where R has a hydrogen that may be replaced by a polymer chain, e.g. aryl, alkyl, but not e.g. F, Br)

The general formula for a polarizable ligand as part of the backbone of a polymer chain is:  $-(R-\text{polarizable ligand}-R)-(Y)-$  wherein Y is a generalized repeat unit.


A specific example of the foregoing is:

21


In structure 21 Y is a generalized repeat unit, and could be, for example, any of the repeat units I-XII below.




I




II




III




IV




V




VI





VII




VIII



IX




XI




XII

where R is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, aryloxy, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkyleneoxy, any two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, r is 0-7, and A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, -PR<sub>1</sub>- and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-, -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, Cl, Br, I, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, and E is selected from the group consisting of O, NH, and S.


The polymers of the present invention are typically aromatic polymers, having relatively short conjugation lengths leading to fluorescence in the blue to ultraviolet region. Preferably the conjugation length will be 2 to 50 conjugated rings, more preferably 3 to 10 conjugated rings, even more preferably 3 to 6 conjugated rings. Some or all of the rings may be part of a fused ring system. Conjugation length, and therefore absorption and emission wavelengths, may be controlled with non-aromatic spacer groups. Non-limiting examples of spacer groups, or repeat units are -O-, -S-, -NR-, -CR<sub>1</sub>R<sub>2</sub>-, -(CH<sub>2</sub>)<sub>n</sub>-, -(CF<sub>2</sub>)<sub>n</sub>-, ester, amide, and the like. The polymers may be homopolymers, or copolymers. The polymers may be linear, branched, hyperbranched, dendritic, crosslinked, random, block, graft, or any structural type. It may be desirable to utilize dendritic or hyperbranched polymers to channel energy into a luminescent metal held at or near the core of the polymer molecules. In this way the luminescent metals are naturally isolated from one another avoiding concentration effects, and may be more evenly distributed in the polymer matrix allowing higher metal concentrations and greater brightness. Examples of polymers are those having repeat units selected from the groups consisting of:




I




II




III




IV




V




VI






VII



VIII



IX



where R is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, aryloxy, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkyleneoxy, any two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, and q is 0-6, A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-, -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, and r is 0-7, and E is selected from the group consisting of O, NH, and S, and one or more fluorescent metal ions.

The molecular weight (MW) of the organic matrix, or aromatic matrix, or aromatic hydrocarbon matrix, will greatly influence the properties of the device and the ease of fabrication of the device. Polymers are used as matrices partly because polymer may be cast into thin films by spin coating, a relatively low cost method. Other methods, such as screen-printing and ink jet printing, also require controlled viscosity of the solution carrying the materials to be printed. Polymers are very effective at controlling the viscosity by adjusting their MW and concentration. The MW of the conjugated polymers will also have an influence on conductivity of the resulting film. The MW should be high, preferably greater than about 30,000 Dalton, more preferably greater than about 50,000 Dalton, even more preferably greater than about 100,000 Dalton, and yet more preferably greater than about 150,000 Dalton, and most preferably greater than about 200,000 Dalton as measured by gel permeation chromatography (GPC) using techniques well known in the art and referenced against polystyrene standards. A high MW will aid in spin coating and printing operations. A high MW will also prevent the material from crystallizing in use, which is detrimental to device performance.

The solution viscosity may also be used as a relative measure of MW. The viscosity may be measured, for example, by using an Ubbelohde viscometer to find




1 the specific viscosity at several concentrations and extrapolating the intrinsic  
viscosity. The intrinsic viscosity of the rigid and semi-rigid polymers of the present  
invention is preferably greater than 0.8 dL/g, more preferably greater than 1 dL/g,  
even more preferably greater than about 1.5 dL/g, and most preferably greater than  
5 about 2 dL/g. Intrinsic viscosity greater than 3 dL/g may also be desirable in certain  
cases. The viscosity of polymers that are not fully conjugated and having non-  
aromatic spacer groups may be lower, preferably greater than 0.3 dL/g, more  
preferably greater than 0.5 dL/g, and most preferably greater than 0.6 dL/g.  
Inherent viscosity is sometimes used as a simpler measure than intrinsic viscosity.  
For the purposes of the present invention, inherent viscosity of greater than 1 is  
10 preferred, more preferably greater than 1.5, even more preferably greater than 2  
dL/g, for rigid or highly conjugated polymers. Lower inherent viscosity is preferred  
for non-rigid, non-fully conjugated polymers, e.g., 0.3 dL/g, more preferably greater  
than 0.5 dL/g, and most preferably greater than 0.6 dL/g.

A polymer matrix may be thermoplastic or thermoset. It may be desirable to  
15 use a crosslinked or thermoset type polymer to improve the stability of an EL layer.  
In this case the metal ion or complex is mixed with a polymer precursor, preferably  
forming a homogeneous mixture, which is then cured using any means known in the  
art, including, but not limited to, thermal, UV, e-beam, microwave, photo, and  
chemical curing. For example, a highly aromatic bisepoxide is blended with a  
20 (optionally highly aromatic) hardener, and a lanthanide metal complex bearing  
aromatic groups. The ligands on the metal complex are chosen such that the metal  
complex remains homogeneously distributed during and after curing the epoxy, and  
do not phase separate. The ligands may also contain thermosetting groups, for  
example, a ligand bearing an epoxy group, which will become part of the polymer  
25 matrix on curing. The ligands are also chosen such that energy transfer from excited  
states of segments of the epoxy chain to the metal complex or ion is efficient. The  
epoxy/hardener/lanthanide metal mixture is then applied as needed, for example, as  
a thin film, and cured. It may be desirable to include a solvent in the  
epoxy/hardener/lanthanide metal mixture to aid film formation, which solvent is  
30 removed before, during, or after curing. Similarly, other thermosetting systems may  
be used, including but not limited to, cyanate ester, ethynyl, maleimide, nadimide,  
olefin/vulcanizer, phenolic, phenyethynyl, silicone, styrenic, urethane, and the like.

The matrix may be oligomeric, that is relatively short chain of repeat units.  
Oligomers may be desired over polymers to achieve lower melt viscosity or ease of  
35 synthesis. Oligomers have advantages over small molecules in that oligomers are  
more readily processed to give amorphous films.

1 The matrix may also be composed of small molecules. It is preferable to use  
molecules or mixtures of molecules that can be processed into amorphous or glassy  
films. For example, it is known in the art that spiro type molecules such as 22 (J.  
Salbeck, J. Bauer, and F. Weissortel, Polymer Preprints, 38, (1) 1997), will form  
5 glassy films that are highly fluorescent. The Salbeck et al. article is incorporated  
herein by this reference.



15 A key feature of the molecules reported by Salbeck et al, are the long arms  
that disrupt crystallinity and provide conjugation. Luminescent metal complexes  
having phenyl, biphenyl, terphenyl, or quaterphenyl groups, preferably terphenyl or  
quaterphenyl groups, will form homogeneous amorphous mixed films with long arm  
spiro molecules. The aromatic groups on the long arm spiro molecule and the  
aromatic ligands enhance energy transfer to the metal from the spiro molecule.  
20 Spiro molecules, such as 22, may be combined with fluorescent metal complexes,  
preferably lanthanide complexes, to form glassy films that fluoresce predominantly  
the color of the fluorescent metal.

25 The organic matrix of the present invention may be an aromatic matrix,  
preferably an aromatic hydrocarbon matrix, containing only carbon and hydrogen,  
and preferably only aromatic rings. The aromatic rings may be phenyl or phenylene,  
or fused ring structures such as naphthalene, anthracene, phenanthrene and the  
like. The aromatic hydrocarbon matrix may be composed of discrete molecules (i.e.,  
having molecules of only a single molecular weight) or may be oligomeric or  
polymeric phenylenes (i.e., having a range of molecular weights). The aromatic  
hydrocarbon matrix may be spiro structures such as structure 22, or fluorene  
30 containing structures such as 9,9-diphenylfluorene. The aromatic hydrocarbon  
matrix may be a mixture of discrete molecules, oligomers, and/or polymers. The  
aromatic matrix may be linear or branched. Non-limiting examples of an aromatic  
matrix are 1,3-di(2-benzoxazole)benzene, 2,4-diphenylquinoline, 2,3-  
35 diphenylquinoxaline, 1,4-di(6-iodo-4-phenylquinolinedi-2-yl)benzene, 6,6'-di(2,4-  
diphenylquinoline), 4,4'-diphenyl-4,4'-dipyridyl, triphenyltriazine, N,N,N',N'-  
tetraphenylbenzidine, poly(4,4'-triphenylamine), tri-1-naphthylamine, polyaniline,  
poly(N-phenylaniline), poly(2,3-dioctyl-1,4-thiophene), poly(2,3-ethylenedioxy-1,4-

1 thiophene) and the like. Non-limiting examples of discrete aromatic hydrocarbon  
molecules are terphenyl, 9,9'-diphenylanthracene, pentacene, tetraphenylethylene,  
triphenylethylene, triphenylmethane, triphenylene, tetraphenylbenzene, and the  
like. Non-limiting examples of oligomeric or polymeric aromatic hydrocarbon  
matrices are poly(phenylphenylene), poly(phenyl-1,4-phenylene-co-phenyl-1,3-  
5 phenylene), hyperbranched polyphenylene, poly(9,9'-dioctylfluorene), and the like.

The organic matrix may be chosen to be an electron or hole transport  
material. Such materials will have a high electron mobility, preferably greater than  
 $10^{-6}$  cm<sup>2</sup>/V-s, more preferably greater than  $10^{-5}$  cm<sup>2</sup>/V-s, and most preferably greater  
than  $10^{-4}$  cm<sup>2</sup>/V-s.

10 A function of the matrix, whether polymeric, oligomeric, or small molecule, is  
to carry charge (holes and/or electrons) and excited state energy (excitons).  
Aromatic, polarizable molecules will have these properties, to an extent dependent  
on their conjugation length, and ability to transfer energy through space; e.g.,  
Förster coupling; see e.g., "Electroluminescent Materials," Blasse and Grabmaier,  
15 Chapter 5, 1994, Springer-Verlag, which is incorporated herein by this reference.

The effectiveness of a matrix to transfer energy to a metal, or the  
effectiveness of a ligand to transfer energy from a matrix to a metal may be  
determined by measurement of spectra. The UV-vis spectrum of the matrix is  
measured and the extinction coefficient at 354 nm (or other particular wavelength,  
20 354 is used because it is easily obtained from a mercury lamp and is in the near UV)  
calculated and noted as  $E_{\text{matrix}}$ .  $E_{\text{matrix}}$  has units of liter/mole-cm. A series of  
photoluminescence spectra of the matrix plus metal complex is taken at a metal  
complex concentration of 0.1 wt% metal and the quantum yield at the wavelength  
maximum in the visible region is calculated for each and noted as  $\Phi_{\text{complex}}$ .  $\Phi_{\text{complex}}$   
25 is unitless. The ratio  $\Phi_{\text{complex}}/E_{\text{matrix}}$  is the figure of merit F. The figure of merit F  
has units of mole-cm/liter. Systems with higher F are better than those with lower  
F. This test may be modified in particular cases, e.g. it may be desired to use lower  
concentrations of metal complex to avoid concentration quenching or higher  
concentrations to improve sensitivity. It may be desirable to integrate the  
30 photoluminescence intensity over a finite wavelength range instead of using the  
wavelength at maximum intensity (Note the units will change accordingly). This test  
measures the combined efficiency of energy transfer from the excited state of the  
matrix to the metal (through ligand or otherwise) and emission from the excited  
metal.

35 The luminescent matrix of the instant invention is useful in  
electroluminescent (EL) devices. In an EL device an EL material is sandwiched  
between two electrodes and a voltage applied. Typically, one of the electrodes is a

1 transparent electrode. Examples of transparent electrodes include, but are not limited to, indium tin oxide (ITO), antimony tin oxide, doped metal oxides such as doped zinc oxide, and doped titanium oxide, polyaniline, PEDOT, very thin metal films such as a 50 nm gold film, and combinations of the above.

5 EL devices may contain additional layers, including, but not limited to hole transport layers (HTL), electron transport layers (ETL), conducting polymer layers (CPL), metal layers, and layers to seal the device from the atmosphere.

10 The devices may have mixed layers, for example a layer comprising a hole transport material and a luminescent material. Or a layer comprising a hole transport material, a luminescent material and an electron transport material. One skilled in the art will know how to select HTL and ETL materials.

15 The devices may have graded or gradient layers. That is, the concentration of a hole transport, a luminescent, or an electron transport material may vary with distance from the electrode in a continuous fashion. Graded layers may be prepared by allowing one layer to diffuse into an underlying layer, or by changing the composition of the layer as it is being deposited.

20 Turning to FIG. 1, there is shown one embodiment of an electroluminescent device 10 provided in accordance with practice of the present invention. The electroluminescent device 10 includes a transparent conductor 12 which acts as a first electrode. A hole transport layer 14 and an electron transport layer 16 supply holes and electrons, respectively, to an electroluminescent layer 18. A second electrode 20 completes the circuit. The electroluminescent device 10, in this embodiment, is mounted on a substrate 22 which, in some embodiments, can be glass. Other substrates such as plastic can be used if desired. The substrates can be transparent, translucent, or opaque. If the substrate is opaque, the top electrode is preferably transparent. Turning now to FIG. 2, there is shown an exploded view of the electroluminescent device 10 of FIG. 1, where like components are labeled with the reference numerals of FIG. 1.

25 Turning to FIG. 3, there is shown an array of cells of electroluminescent devices 30 provided in accordance with practice of the present invention. Each of the electroluminescent devices comprises two electrodes 32 and 34 with an electroluminescent layer 36 sandwiched therebetween. Optionally, a hole transport layer and/or an electron transport layer can be provided on each side of the electroluminescent layer. A driver circuit 40 supplies current to the top electrodes 32. Current-carrying lines 42 are connected to the bottom electrodes 34, and address lines 44 are used to control the current supplied through the driver circuitry 40 and drivelines 46. Each cell may have a different electroluminescent material in the layer 36 to thereby emit a different color. The array shown in FIG. 3 is merely


illustrative, and the geometry of the array provided in accordance with the present invention is not limited by the arrangement of the drawing.

Turning now to FIG. 4, there is shown an electroluminescent device 50 provided in accordance with practice of the present invention which comprises a bottom electrode 52, a top electrode 54, an electron transport layer 56, and an electroluminescent layer 58 mounted on a substrate 60. In this embodiment, there is no hole transport layer, and the electrode 54 supplies current through the electron transport layer 56.

Turning now to FIG. 5, there is shown yet another embodiment of an electroluminescent device 70 provided in accordance with practice of the present invention. The electroluminescent device 70 incorporates a graded electroluminescent layer 72 sandwiched between electrodes 74 and 76. The electroluminescent device 70 is supported on a substrate layer 78. In this embodiment, the graded layer comprises an organic matrix and a luminescent metal ion or luminescent metal complex, and optionally a hole transport material and/or an electron transport material. The concentration of the luminescent metal ion or luminescent metal complex is dependent on position, for example the concentration may be low, or approach zero near the electrodes 74 and 76, and be highest at the center of the layer 72. This arrangement would prevent quenching of luminescence by the electrodes. Similarly, a gradient of hole transport material, e.g. varying approximately linearly from zero near the electrode 74 to the highest near the electrode 76, would aid in hole transport from electrode 76, but not allow holes to reach the electrode 74. Similarly, a gradient of electron transport material from zero near the electrode 76, and highest near the electrode 74, would aid electron transport.


In the absence of an electron transport layer and/or a hole transport layer, the organic matrix comprising the electroluminescent layer must carry electrons and/or holes respectively.

#### Example 1.



Polymer 23 poly-p-(N,N-dimethylamidophenylene) (10 mg) is prepared (as described in U.S. Patent No. 5,227,457 Example XV, incorporated herein by reference) by placing dry nickel chloride (60 mg., 0.46 mmol), triphenylphosphine (0.917 g, 3.5 mmol), 2,2'-bipyridine (64.7 mg, 0.41 mmol), sodium iodide (0.39 g, 1.44 mmol), and zinc powder (0.92 g, 14.1 mmol) into a 100 ml round-bottom flask. The flask and its contents are heated to 50°C for 90 minutes under dynamic vacuum to remove trace water. Evacuation is discontinued, and argon is admitted to the flask. Dry dimethylformamide (DMF) (8 ml) is added, and the temperature is raised to 80°C. Within 5 minutes, the mixture turns a deep-red color. After stirring for 20 minutes under argon, a solution of 2,5-dichloro-N,N-dimethylbenzamide (2.016 g, 9.1 mmol) in DMF (5 ml) is added. After 2 hours, the mixture is cooled to room temperature, then poured into 200 ml of 15% aqueous HCl and extracted with benzene. The product, as a suspension in benzene, is washed with 5% HCl. Dichloromethane is added to the thick, white, benzene suspension to give a slightly cloudy solution, which is separated from the remaining water and taken to dryness on a rotary evaporator to give 0.5 g of poly-p-(N,N-dimethylamidophenylene), a white powder. The polymer 23 was dissolved in 1.5 g N-methyl pyrrolidinone (NMP). Separately 15 mg  $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$  was dissolved in 1.7 g NMP. The solutions were mixed and stirred for two minutes at about 120°C. A portion of this solution was cast onto a microscope slide on a hot plate in air at 120-130°C. An essentially dry film was obtained after a few minutes. Upon exposure of this film to long wavelength UV radiation (~366 nm) red luminescence was observed. As a standard reference, 15 mg of polymer 23 was dissolved in 1.2 g NMP and cast as above. Upon exposure to long wavelength UV radiation, bright blue luminescence was observed. The red luminescence of the polymer 23/ $\text{Eu}^{3+}$  film diminished when placed in air for an extended period of time. A drop of water was placed on the film. The region of the film contacted by water fluoresced blue.

#### Example 2.




Structure 24

Poly(1,3-(5-dimethylamino)phenylene), 24

To N,N-dimethyl-3,5-dichloroaniline (1.90 grams, 0.01 mol) in anhydrous NMP (50 ml) is added nickel(bis(triphenylphosphine)dichloride) (0.109 g, 0.167 mmol), sodium bromide (0.103 g, 1 mmol), and triphenylphosphine (0.262 g, 1 mmol), and zinc dust (1.96 g 0.03 mol) under nitrogen. On addition of zinc the reaction mixture warms. The temperature is held between 70°C and 85°C using a cooling or heating bath as needed, for 4 hours. The reaction mixture is then cooled to below 50°C and poured into 100 ml of isopropanol. The coagulated polymer is filtered and re-dissolved in NMP. The solution is filtered to remove zinc, and coagulated a second time into isopropanol. The coagulated polymer is filtered and dried.

Polymer 24 poly(1,3-(5-dimethylamino)phenylene) (12 mg) is dissolved in 1.2 g NMP. 10 mg  $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$  is dissolved in 1.2 g NMP. Half of each solution is mixed together and cast as in Example 1. The other half of polymer PP3 solution is separately cast and dried. Upon exposure to long wavelength UV radiation, the film of pure PP3 luminescence blue while the film of the PP3/  $\text{Eu}^{3+}$  does not luminesce.

#### Example 3.



Structure 25

Poly(2,5-benzophenone-co-1,4-phenylene-co-1,3-phenylene), 25

The following compounds were added to a round bottom flask under a nitrogen purge: 2,5-dichlorobenzophenone (1.51 grams, 6.00 mmol), 1,4-dichlorobenzene (0.88 gram, 6.00 mmol), 1,3-dichlorobenzene (7.06 ml, 48 mmol), NMP (53.9 ml), NaI (0.84 gram, 5.60 mmol), triphenylphosphine (3.15 gram, 13.6 mmol), nickelbis(triphenylphosphine)dichloride (0.523 gram, 0.800 mmol), and Zn dust (5.6 gram, 85.6 mmol). The reaction was heated in an oil bath set to 65°C. The temperature of the reaction mixture increased to 81.1°C and then returned to 65°C. The reaction mixture was held at 65°C overnight, after which time the mixture was coagulated into a mixture of ethanol and concentrated hydrochloric acid. The

1 coagulated polymer was washed with hot ethanol and hot acetone and dried. The weight average molecular weight was determined to be 32,333 by gel permeation chromatography (GPC). The yield was 5.265 grams of polymer 25 indicating that some impurities were still present in the coagulated polymer. Films were cast from hot NMP. The films fluoresce blue under long wave ultraviolet irradiation.

5 Polyphenylene polymer 25 20 (mg) is dissolved in 1.5 g NMP. Separately, 10 mg  $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$  is dissolved in 1.2 g NMP. The solutions are mixed and cast as in Example 1. Upon exposure to UV radiation (366 nm) the typical blue luminescence of polymer 25 is observed with no observable diminution in strength or shift in color due to the addition of europium salt.

10 In Examples 1 and 2, and most notably Example 1, the color of luminescence of the mixture was altered from the blue color of the host polymer, most probably due to energy transfer from the excited state of the polymer to the rare earth metal and the subsequent emission from the metal ion. The red emission in Example 1 indicates emission only from the excited  $\text{Eu}^{3+}$  ions and the transfer of energy from the excited state of 23 to the  $\text{Eu}^{3+}$  ions.

15 Complexation or coordination of the rare earth ion and the polymer appears to be important for energy transfer. Polymers 23 and 24 contain amide and amine moieties in their structure while polymer 25 is purely a hydrocarbon. Complexation of the nitrogen or oxygen containing polymers seems to facilitate energy transfer. In Example 3, Polymer 25 does not contain groups that interact strongly with the europium ion and thus interaction and energy transfer did not take place. In Example 2 polymer 24 has an amine side group which may coordinate to a metal ion. Energy was transferred from the polymer as indicated by quenching of polymer luminescence, however, luminescence of the europium is not observed, indicating that other factors may cause quenching of the rare earth luminescence.

#### Example 4. Polyfluorene 26.

30 9,9-di-n-butyl-2,7-dibromofluorene 27 is prepared by the method of Woo, et al, U.S. 5,962,631 the relevant parts of which are incorporated herein by reference. The GPC molecular weight of the polymer 27 is 50,000 to 60,000.

35 To 27 (4.36 grams, 0.01 mol) in anhydrous NMP (50 ml) is added nickel(bis(triphenylphosphine)dichloride (0.109 g, 0.167 mmol), sodium bromide (0.103 g, 1 mmol), and triphenylphosphine (0.262 g, 1 mmol), and zinc dust (1.96 g, 0.03 mol) under nitrogen. On addition of zinc the reaction mixture warms. The temperature is held between 70°C and 85°C using a cooling or heating bath as




needed, for 4 hours. The reaction mixture is then cooled to below 50°C and poured into 100 ml of isopropanol. The coagulated polymer is filtered and redissolved in NMP. The solution is filtered to remove zinc, and coagulated a second time into isopropanol. The coagulated polymer 26 is filtered and dried.

Example 5. Polyfluorene copolymer 28

9,9-di-n-butyl-2,7-dibromofluorene 27 is prepared as above by the method of Woo, et al, U.S. 5,962,631.

2,7-dibromofluorene-9-spiro-2'-(1',3',6',9',12',15'-hexaoxacycloheptadecane), 29



To a solution of 2,7-dibromo-9-fluorenone (33.8 grams, 0.1 mol) in toluene (250 ml), is added penta(ethylene glycol) (23.8 grams, 0.1 mol), and DOWEX® 50WX4-100 ion-exchange resin (5 grams). The mixture is gently refluxed for 8 hours in a dean-stark apparatus to remove water, after which time the mixture is cooled to room temperature and the ion-exchange resin is filtered off. The solvent is removed by distillation at reduced pressure using a rotary evaporator. The resulting product may be used as is or purified by column chromatography.

Alternatively, the crown ether 29 may be prepared following the method of Oshima et al, Bull. Chem. Soc. Japan, 59, 3979-3980, except replacing 9-fluorenone with 2,7-dibromo-9-fluorenone.

To 29 (5.58 grams, 0.01 mol) in anhydrous NMP (50 ml) is added 27 (4.36 grams, 0.01 mol), nickel(bis(triphenylphosphine)dichloride (0.109 g, 0.167 mmol), and triphenylphosphine (0.262 g, 1 mmol), and zinc dust (1.96g, 0.03 mol) under

nitrogen. On addition of zinc the reaction mixture warms. The temperature is held between 70°C and 85°C using a cooling or heating bath as needed, for 4 hours. The reaction mixture is then cooled to below 50°C and poured into 100 ml of isopropanol. The coagulated polymer 28 is filtered and redissolved in NMP. The solution is filtered to remove zinc, and coagulated a second time into isopropanol. The coagulated polymer is filtered and dried.

#### Examples 6-8. Polyfluorene type fluorophors.

Polyfluorene 28 (10.0 grams) and a metal salt as indicated in Table 1 are dissolved in 100 ml NMP. The solution is spin-coated onto an ITO coated glass substrate to a thickness of about 100 nm. The coated substrate is dried at 100°C at reduced pressure for 3 hours. The films fluoresce as indicated in Table 1 when irradiated at 366 nm. An aluminum layer of a thickness of about 200 nm is evaporated onto the polymer/metal salt film at about  $10^{-6}$  torr. Connections were made to the ITO and aluminum layer with indium-tin solder. A potential is applied to the films with ITO positive and aluminum negative (forward bias), causing the devices to emit light of a color corresponding to the photoluminescence.

**TABLE 1**

Example	Metal Salt	Weight	Moles	Luminescence
Example 6	Tb(NO <sub>3</sub> ) <sub>3</sub> ·5H <sub>2</sub> O	4.35 grams	0.01 mol	Green
Example 7	Ce(NO <sub>3</sub> ) <sub>3</sub> ·6H <sub>2</sub> O	4.34 grams	0.01 mol	Blue
Example 8	Eu(NO <sub>3</sub> ) <sub>3</sub> ·5H <sub>2</sub> O	4.28 grams	0.01 mol	Red

#### Examples 9-11. Films of polyfluorene and a polarizable fluorescent metal complex.

Polyfluorene 28 (10.0 grams), and a metal complex as indicated in Table 2 (dbm is dibenzoylmethane) are dissolved in 100 ml NMP. The solution is spin-coated onto an ITO coated glass substrate to a thickness of about 100 nm. The coated substrate is dried at 100°C at reduced pressure for 3 hours. The films fluoresce as indicated in Table 2 when irradiated at 366 nm. An aluminum layer of a thickness of about 200 nm is evaporated onto the polymer/metal salt film at about  $10^{-6}$  torr. The area covered by the aluminum is controlled using a mask of 1 cm<sup>2</sup> open area. Connections were made to the ITO and aluminum layer with indium-tin solder. A potential is applied to the films with ITO positive and aluminum negative (forward bias), causing the devices to emit light of a color corresponding to the photoluminescence.

TABLE 2

Example	Metal Complex	Weight	Moles	Luminescence
Example 9	Eu(dbm) <sub>3</sub>	8.25 grams	0.01 mol	Red
Example 10	Tb(dbm) <sub>3</sub>	8.32 grams	0.01 mol	Green
Example 11	Ce(dbm) <sub>3</sub>	8.13 gram	0.01 mol	Blue

## Example 12.

Europium doped yttria, Y<sub>2</sub>O<sub>3</sub>:Eu (100 grams) (Superior MicroPowders, Albuquerque, NM) is added to a solution of polymer 23 (100 grams) in NMP (1 liter). The suspension is mixed well and films are cast onto ITO coated glass substrates to give films of thickness of about 2 microns. An aluminum contact is evaporated onto the film through a mask to cover a 1-cm square section of the film. Under forward bias the film emits red light.

Examples 13-16. Nanocrystalline phosphor/polymer matrix type electroluminescent systems.

Nanocrystalline phosphors are prepared according to Ihara et al, as reported in Society for Information Display, International Symposium, 1999. The average particle size is 2 to 3 nanometers. Ten grams of nanocrystalline phosphor is added to 5 grams of polymer 26 (or polymer 23) in 50 ml of NMP. The resulting suspensions are spin cast onto ITO coated glass plates to form thin films between 100 and 500 nanometers. The films fluoresce (PL) under 366-nm irradiation as tabulated in Table 3. The films are then coated with aluminum by vacuum evaporation through a mask with a 5-mm by 10-mm hole. A voltage of 5 to 10 V is applied across the device with the ITO electrode being positive causing electroluminescence (EL) as listed in Table 3.

TABLE 3

Example	Nanocrystal	Polymer	PL	EL
Example 13	ZnS:Eu	<u>26</u>	Red	Red
Example 14	ZnS:Tb	<u>26</u>	Green	Green
Example 15	ZnS:EuF <sub>3</sub>	<u>23</u>	Red	Red
Example 16	ZnS:TbF <sub>3</sub>	<u>26</u>	Green	Green

# Examples 17-20. Polymer / Rare Earth Metal Complexes

Energy transfer between an aromatic polymer and lanthanide ions was qualitatively examined. NMP was used as co-solvent for all mixtures from which films were cast and dried at around 100°C in air. Dilute and approximately equivalent concentration solutions of all species were made in NMP. Desired solution mixtures were then prepared by mixing of equivalent amounts of the polymer and metal salt solutions. Films were prepared by casting these solution mixtures onto slides and drying in air at ~100°C using a hot plate. The dried films were then excited with long wave UV radiation (366 nm) and the luminescence observed. Table 4 shows the luminescence properties of the starting materials. Table 5 summarizes the results for the mixtures.

Table 4

Material	Phase	Luminescence Color	Comments
<u>25</u>	Solid	Blue	Hazy film
<u>23</u>	Solid	Blue	Clear film
<u>24</u>	Solid	Blue	Clear brownish
EuCl <sub>3</sub>	Solution	Red	Clear solution
TbCl <sub>3</sub>	Solution	Green	Clear solution

Table 5

Example #	Mixtures	Phase	Luminescence / Color	Comments
17	<u>25</u> + Eu <sup>3+</sup>	Solid	Blue	Hazy film
18	<u>23</u> + Eu <sup>3+</sup>	Solid	Red	Clear film
19	<u>24</u> + Eu <sup>3+</sup>	Solid	None	Clear brownish
20	<u>23</u> + Tb <sup>3+</sup>	Solid	Weak Blue	Clear

In Examples 18, 19, and 20 the color of the film fluorescence is altered away from the blue color of the sensitizer or host polymer, most probably due to energy transfer from the excited state of the polymer to the rare earth metal and the subsequent emission from the lattice of the metal ion. This was most pronounced in Example 18 where the red color indicated emission only from the excited Eu<sup>3+</sup> ions and the transfer of energy from the excited state of polymer 23 to the Eu<sup>3+</sup> ions. In example 19 the fluorescence of the polymer was quenched indicating energy transfer, however, the Eu fluorescence in the red was too weak to be visible. In Example 20,

1 the weak blue fluorescence indicated only partial energy transfer to Tb, and the green color of Tb fluorescence was not observed. In this set of experiments the N,N-dimethylamido groups of polymer 23 was most effective at transferring energy to  $\text{Eu}^{3+}$ .

5 Example 21. Crosslinked matrix

The bisglycidylether of 4,4'-biphenyl is mixed with 20 mole% of 1-naphthylamine, 500 mole% anisole, and 2 mole% of  $\text{Eu}(\text{acac})_3$ . Optionally, 10 to 50 mole% of a polymer of structures I through XII is added. The mixture is cast into a film and heated to 80°C under reduced pressure causing simultaneous evaporation of anisole and curing of the epoxy groups. The cured film fluoresces red.

Example 22. Photocrosslinked matrix

15 Monomers 1-vinylnaphthalene (0.1 mol) and divinylbenzene (0.005 mol), photoinitiator (0.001 mol), and tris(8-hydroxyquinolino)terbium, are mixed and cast as a thin film by spin coating onto an ITO coated glass substrate. The film is immediately exposed to 254 nm light to activate the photoinitiator. The film is then heated to 100°C for 5 min to remove unreacted monomer. The film fluoresces green. A second electrode of aluminum is deposited onto the luminescent layer by sputtering.

Example 23. Photocrosslinked matrix

25 The same as example 22, except that polystyrene (0.05 mol) is added to the mixture before spin coating to adjust the viscosity of the mixture.

Example 24. Small molecule matrix - spiro compound matrix


30 The spiro compound 22 (0.1 mol) is dissolved in a mixture of toluene (50 ml) and tetrahydrofuran (50 ml) and tris(benzoylnaphthoylmethane)terbium (0.05 mol) and polystyrene (0.01 mol) are added. The resulting mixture is spin coated onto the top of a multilayer structure consisting of glass, ITO, and tris(4-phenylethynylphenyl)amine cured at 300°C for 1 hour under nitrogen (50 nm). The resulting multilayer structure fluoresces green. A top electrode is formed by evaporation of aluminum.

1 Tris(4-phenylethynylphenyl)amine.

Tri(4-bromophenyl)amine (0.1 mol) and phenylacetylene (0.3 mol) are allowed to react in NMP (100 ml) with palladium diacetate (0.006 mol), tritolylphosphine (0.012 mol) and triethylamine (0.3 mol) at 80°C for 16 hours. The triethylammonium bromide is filtered off and the product is purified by recrystallization from hexane.

Example 25.

Monomer 27 (9,9-di-n-butyl-2,7-dibromofluorene) (43.6 gram, 0.1 mol) and 2,7-dibromo-9-fluorenone (8.45 grams, 0.025 mol) are polymerized using the conditions of Example 5 to give copolymer 30 having the following structure:



A film is cast from a solution of 30 (1 gram) and europium trichloride hydrate (0.1 gram) in NMP (10 ml). The film fluoresces red.

Example 26. Film containing hole transport agent

The method of Example 1 is repeated except that N,N'-diphenyl-N,N'-bis(3-methylphenyl)-(1,1'-biphenyl)-4,4'-diamine (TPD) 5 mg is added to the first solution in addition to polymer 23. The resulting film has a red fluorescence when irradiated at 366 nm.

Example 27.

Poly(para-benzoylmorpholine) 31 is prepared (as described in U.S. Patent No. 5,227,457 Example XVII incorporated herein by reference) by placing anhydrous nickel(II) chloride (50 mg, 0.39 mmol), triphenylphosphine (750 mg, 2.86 mmol), sodium iodide (150 mg, 1.0 mmol), and 325 mesh activated zinc powder (1.2 g, 18 mmol) into a 25 ml flask under an inert atmosphere along with 5 ml of anhydrous N-methyl-pyrrolidinone (NMP). This mixture is stirred at 50°C for about 10 minutes,

1 leading to a deep-red coloration. A solution of 3 g (11.5 mmol) of 2,5-  
dichlorobenzoylmorpholine (>99% pure by HPLC analysis) in 10 ml of anhydrous  
NMP is then added by syringe. After stirring for about 60 hours, the resulting  
highly viscous solution is poured into 100 ml of 1 molar hydrochloric acid in ethanol  
5 to dissolve the excess zinc metal and to precipitate the polymer. This suspension is  
filtered, and the precipitate triturated with acetone to afford, after isolation and  
drying, 2.2 g (100% yield) of polyparabenzoylmorpholine as a light tan powder. The  
inherent viscosity is about 1.8 dL/g. Polymer 31, 10 mg, is dissolved in 1.5 g NMP.  
Separately, 15 mg  $\text{Eu}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$  and 6 mg phenanthroline are dissolved in 1.5 g  
10 NMP. The solutions are mixed and stirred for two minutes at 120°C. A portion of  
the solution is cast onto a glass plate at 120-130°C, and kept hot until dry, and then  
cooled to room temperature. On exposure to 366 nm UV radiation, red luminescence  
is observed. A film prepared similarly from a solution containing polymer 31 alone  
fluoresces blue.

15 Example 28.

Copoly- $\{1,4\text{-(benzoylphenylene)}\}\text{-}\{1,4\text{-phenylene}\}$  32 is prepared (as described in U.S.  
Patent No. 5,227,457 Example XVII incorporated herein by reference) by placing  
anhydrous bis(triphenylphosphine) nickel(II) chloride (3.75 g; 5.7 mmol),  
20 triphenylphosphine (18 g; 68.6 mmol), sodium chloride (2.0 g, 34.2 mmol), 325 mesh  
activated zinc powder (19.5 g; 298 mmol), and 250 mL of anhydrous NMP into an  
oven dried 1-liter flask under an inert atmosphere. (Activated zinc powder is  
obtained after 2-3 washings of commercially available 325 mesh zinc dust with 1  
molar hydrogen chloride in diethyl ether (anhydrous) and drying in vacuo or under  
25 inert atmosphere for several hours at about 100° -120° C. The resulting powder  
should be sifted (e.g. a 150 mesh sieve seems to be satisfactory), to remove the larger  
clumps that sometimes form, to assure high activity. This material should be used  
immediately or stored under an inert atmosphere away from oxygen and moisture)  
this mixture is stirred for about 15 minutes, leading to a deep-red coloration. A  
30 mixture of 2,5-dichlorobenzophenone (45 g; 179 mmol) and 1,4-dichloro-benzene  
(2.95 g; 20 mmol) is then added to the flask. The temperature of the vigorously  
stirred reaction mixture is held at 60°-70°C until the mixture thickens (about 30  
minutes). After cooling the reaction mixture to room temperature overnight, the  
resulting viscous solution is poured into 1.2 L of 1 molar hydrochloric acid in ethanol  
35 to dissolve the excess zinc metal and to precipitate the polymer. This suspension is  
filtered and the precipitate is washed with acetone and dried to afford crude resin.  
To achieve high purity, the crude polymer is dissolved in about 1.5 L of NMP and

1 coagulated into about 4 L of acetone, continuously extracted with acetone, and dried to afford 30 g (89% yield) of an off-white powder. The intrinsic viscosity is 4.2 dL/g in 0.05 molar lithium bromide in NMP at 40°C.

5 Polymer 32, 1.3 g is reduced using sodium borohydride (1.1 molar equivalent of sodium borohydride for each benzoyl group of 32) in phenethylalcohol, to give polymer 33. Polymer 33 is treated with an excess of acetic anhydride to esterify the alcohol groups resulting from the sodium borohydride reduction, to give polymer 34.

10 A layer of polymer 34 (about 300 nm thick) is spin cast onto a glass substrate coated with an indium tin oxide transparent conductive layer, which has been coated with Baytron P® (Bayer) of thickness about 500 nm. A layer of calcium is evaporated on top of the layer of polymer 34 as a cathode. Finally, a layer of magnesium is evaporated on top of the calcium to protect the calcium from air. When a voltage is applied between the indium tin oxide anode and the calcium cathode, blue light is  
15 emitted.

#### Example 29.

20 Copoly-{1,4-(benzoylphenylene)}-{1,3-phenylene} 35 is prepared (as described in U.S. Patent No. 5,654,392 Example 16 incorporated herein by reference) by placing anhydrous bis(triphenylphosphine) nickel(II) chloride (10 g; 15 mmol), triphenylphosphine (50 g; 0.19 mole), sodium iodide (15 g; 80 mmol), and 325 mesh activated zinc powder (60 g; 0.92 mole) into a bottle under an inert atmosphere and added to an oven dried 2-liter flask containing 800 milliliters of anhydrous NMP,  
25 against a vigorous nitrogen counterflow. This mixture is stirred for about 15 minutes, leading to a deep-red coloration. A mixture of 2,5-dichlorobenzophenone (127 g; 0.51 Mole) and 1,3-dichlorobenzene (11 ml; 96 mmol) is then added to the flask. After an initial slight endotherm (due to dissolution of monomer), the temperature of the vigorously stirred reaction mixture warms to about 80°-85°C over  
30 30 minutes. After stirring for an additional 10-15 minutes, the viscosity of the reaction mixture increases drastically and stirring is stopped. After cooling the reaction mixture to room temperature overnight, the resulting viscous solution is poured into 6 L of 1 molar hydrochloric acid in ethanol to dissolve the excess zinc metal and to precipitate the polymer. This suspension is filtered, and the  
35 precipitate is continuously extracted with ethanol and then with acetone and dried to afford 93 g (94% yield) of crude white resin. To achieve high purity, the crude polymer is dissolved in about 600 mL of methylene chloride, pressure filtered



1 through 1.2 micron (nominal) polypropylene fiber filters, coagulated into about 2 liters of acetone, continuously extracted with acetone, and dried to afford 92 g (93% yield) of a fine white powder. The GPC MW relative to polystyrene is 150,000-200,000.

5 Polymer 35, 2 g is reduced using sodium borohydride (2 molar equivalent of sodium borohydride for each benzoyl group of 35) in phenethylalcohol to give polymer 36. Polymer 36 is treated with an excess of acetic anhydride to esterify the alcohol groups resulting from the sodium borohydride reduction to give polymer 37. Polymer 37 has a GPC MW of 150,000-200,000 relative to polystyrene. Polymer 37  
10 fluoresces blue when irradiated at 366 nm. A layer of polymer 36 (about 250 nm thick) is spin cast onto a glass substrate coated with an indium tin oxide transparent conductive layer, which has been coated with Baytron P® (Bayer) of thickness about 500 nm. A layer of calcium is evaporated on top of the layer of polymer 36 as a cathode. Finally, a layer of magnesium is evaporated on top of the calcium to protect  
15 the calcium from air. When a voltage is applied between the indium tin oxide anode and the calcium cathode, blue light is emitted.









#### Example 30.



20 Polymer 37 as prepared in Example 28 above, 1 g, is mixed with 0.4 g  $\text{Eu}(\text{NO}_3)_3 \cdot 6\text{H}_2\text{O}$  and 0.15 g phenanthroline in 15 ml NMP. This solution is spin cast onto glass plates pre-coated with indium tin oxide and Baytron P® Bayer to give a film of about 200 nm thick. The film fluoresces red when irradiated at 366 nm. A magnesium/silver cathode is evaporated on top of the polymer 37 layer on one of the  
25 plates. On a second plate, a 100 nm layer of 2,4-dinaphthyloxodiazole is evaporated onto the layer of polymer 37, followed by evaporation of a magnesium/silver cathode. Both devices emit red light when a voltage is applied across the anode and cathode.

30 The above descriptions of exemplary embodiments of photoluminescent and electroluminescent compositions, the process for producing such compositions, and the photoluminescent and electroluminescent devices produced thereby are for illustrative purposes. Because of variations which will be apparent to those skilled in the art, the present invention is not intended to be limited to the particular embodiments described above. The scope of the invention is defined in the following  
35 claims:


## WHAT IS CLAIMED IS:

1. A composition comprising a polymer comprising repeat units selected from the group consisting of:





XI



XII

where R is independently selected from H, D, F, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, aryloxy, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy, any two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, and q is 0-6, A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-, -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, and r is 0-7, and E is selected from the group consisting of O, NH, and S; and

one or more luminescent metal ions or luminescent metal ion complexes.

2. The composition of claim 1, wherein the luminescent metal ion or luminescent metal ion complex comprises a lanthanide metal ion.

3. The composition of claim 1, wherein the polymer is a copolymer.

4. The composition of claim 1, wherein the polymer is a dendritic or hyperbranched polymer.

5. The composition of claim 1, wherein said polymer comprises repeat units of structure II.

6. The composition of claim 1, wherein the luminescent metal ion or luminescent metal ion complex comprises cerium.

1           7.     The composition of claim 1, wherein the luminescent metal ion or  
luminescent metal ion complex comprises europium.

          8.     The composition of claim 1, wherein the luminescent metal ion or  
luminescent metal ion complex comprises terbium.

5           9.     The composition of claim 1, wherein the polymer is a copolymer.

          10.    The composition of claim 9, wherein one of the repeat units has  
structure II.

10          11.    The composition of claim 10, wherein for one of the repeat units having  
structure II q is 0, A is  $-CR_1R_2-$ , and  $R_1$  and  $R_2$  are alkyl.

15          12.    The composition of claim 11, wherein a second repeat unit has  
structure II, wherein q is 0, A is  $-CR_1R_2-$ , and  $R_1$  and  $R_2$  are independently selected  
from the group consisting of H, D, F, alkyl, aryl, alkyleneoxy, polyalkyleneoxy,  
alkoxy, aryloxy, fluoroalkyl, and fluoroaryl.

20          13.    The composition of claim 1, wherein the luminescent metal ion or  
luminescent metal ion complex is present as part of an inorganic solid.

          14.    The composition of claim 13, wherein the inorganic solid is a nanosized  
powder with physical dimensions in the 1 to 1000 nanometer range.

25          15.    The composition of claim 14, wherein the inorganic solid is a  
semiconductor.

          16.    The composition of claim 15, wherein the semiconductor is a II-VI  
semiconductor.

30          17.    The composition of claim 1, wherein the luminescent metal ion or  
luminescent metal ion complex comprises a metal ion selected from the group  
consisting of chromium, manganese, iron, cobalt, molybdenum, ruthenium, rhodium,  
palladium, silver, tungsten, rhenium, osmium, iridium, platinum, gold, and  
35 uranium.

          18.    An electroluminescent device comprising the composition of claim 1.

1

19. The composition of claim 13, wherein the inorganic solid is a semiconductor.

5

20. The composition of claim 19, wherein the semiconductor is a II-VI semiconductor.

10

21. The composition of claim 1 having emission bands of 20 nm or less.

22. The composition of claim 1 having emission bands of 10 nm or less.

23. The composition of claim 1 having emission bands of 5 nm or less.

24. The composition of claim 1 having emission bands of 3 nm or less.






15

25. The composition of claim 1, wherein the luminescent metal ion or luminescent metal ion complex comprises a polarizable ligand.




20

26. The composition of claim 25, wherein the polarizable ligand is selected from the group consisting of:












25



30



35

910111213141516171819

27. The composition of claim 25, wherein the polarizable ligand is part of a polymer chain.

28. The composition of claim 27, wherein the polymer chain is a conjugated polymer chain.

- 1           29.    The composition of claim 1, wherein the polymer is a crosslinked polymer.
30.    The composition of claim 1, wherein the polymer is an oligomer.
- 5           31.    The composition of claim 1, wherein the polymer is a branched polymer.
32.    The composition of claim 1, wherein the polymer is a block co-polymer.
- 10          33.    The composition of claim 1, wherein the polymer is a random co-polymer.
34.    The composition of claim 1, wherein the polymer is a graft co-polymer.
- 15          35.    The composition of claim 1, wherein the conjugation length of the polymer is controlled with non-aromatic spacer groups. .
36.    The composition of claim 35, wherein the spacer groups are selected from the group consisting of -O-, -S-, -NR-, -CR<sub>1</sub>R<sub>2</sub>-, (CH<sub>2</sub>)<sub>n</sub>-, -(CF<sub>2</sub>)<sub>n</sub>-, ester, and amide.
- 20               37.    The composition of claim 35, wherein the conjugation length is between 2 and 50 conjugated rings.
- 25          38.    The composition of claim 35, wherein the conjugation length is between 3 and 10 conjugated rings.
39.    The composition of claim 36, wherein the conjugation length is between 3 and 6 conjugated rings.
- 30               40.    An electroluminescent device comprising the composition of claim 1.
41.    The electroluminescent device of claim 40, wherein the polymer is a crosslinked polymer.
- 35

1           42.    An electroluminescent device comprising:  
              a first electrode;  
              one or more charge transport materials; and  
              an electroluminescent layer comprising the composition of claim 1 and  
5           a second electrode.

          43.    The electroluminescent device of claim 42, wherein one or both of said  
electrodes is a transparent electrode.

10           44.    The electroluminescent device of claim 42, wherein one or both of said  
electrodes comprises tin oxide or doped tin oxide.

          45.    The electroluminescent device of claim 42, wherein one of the charge  
transport materials is a hole transport material provided as a distinct layer.

15           46.    The electroluminescent device of claim 42 comprising two layers; a first  
layer comprising a hole transport material, and the electroluminescent layer which  
comprises an electron transport material.

20           47.    The electroluminescent device of claim 42, wherein an electron  
transport material is provided as a distinct layer.

          48.    The electroluminescent device of claim 42 comprising two layers; a first  
layer comprising an electron transport material, and the electroluminescent layer  
which comprises a hole transport material.

25           49.    The electroluminescent device of claim 42 comprising three layers, the  
electroluminescent layer sandwiched between a layer of electron transport material  
and a layer hole transport material.

30           50.    The electroluminescent device of claim 49, wherein the layers are not  
distinct, but graded.

35           51.    The electroluminescent device of claim 42 comprising a hole transport  
material and an electron transport material both of which are graded in the  
electroluminescent layer.



1           52.    The electroluminescent device of claim 42, wherein the emission bands  
are 20 nm or less.

          53.    The electroluminescent device of claim 42, wherein the emission bands  
are 10 nm or less.

5           54.    The electroluminescent device of claim 42, wherein the emission bands  
are 5 nm or less.

10          55.    The electroluminescent device of claim 42, wherein the emission bands  
are 3 nm or less.

          56.    The electroluminescent device of claim 42, wherein the  
electroluminescent layer comprises a nanosized powder with physical dimensions in  
the 1 to 1000 nanometer range.

15          57.    The electroluminescent device of claim 42, wherein the turn-on voltage  
is less than 15V.

20          58.    The electroluminescent device of claim 42, wherein the turn-on voltage  
is less than 10V.

          59.    The electroluminescent device of claim 42, wherein the turn-on voltage  
is less than 5V.

25          60.    An electroluminescent composition comprising:  
                  an aromatic hydrocarbon matrix; and  
                  a lanthanide metal complex having an aromatic ligand.

30          61.    The composition of claim 60, wherein said aromatic ligand has a diaryl  
group.

          62.    The composition of claim 60, wherein said aromatic ligand has a two  
ring fused ring group.

35          63.    The composition of claim 60, wherein said aromatic ligand has a triaryl  
group.

1           64.    The composition of claim 60, wherein said aromatic ligand has a three  
ring fused ring group.

          65.    The composition of claim 60, wherein said aromatic ligand has a  
polyaryl group.

5           66.    An electroluminescent device comprising the composition of claim 60.

          67.    An electroluminescent device comprising:  
                a first electrode;  
10               one or more charge transport layers; and  
                an electroluminescent layer comprising the composition of claim 60 and  
a second electrode.

          68.    The electroluminescent device of claim 67, wherein one or both of said  
15 electrodes is a transparent electrode.

          69.    The electroluminescent device of claim 67, wherein one or both of said  
electrodes comprises tin oxide or doped tin oxide.

20          70.    The electroluminescent device of claim 67, wherein one of the layers is  
a hole transport layer.

          71.    The electroluminescent device of claim 67, wherein one of the layers is  
a hole transport layer and another of the layers is a mixed layer comprising a  
25 luminescent material and an electron transport material.

          72.    The electroluminescent device of claim 67, wherein one of the layers is  
an electron transport layer.

30          73.    The electroluminescent device of claim 67, wherein one of the layers is  
an electron transport layer and another of the layers is a mixed layer comprising a  
luminescent material and a hole transport material.


          74.    The electroluminescent device of claim 67, wherein one of the layers is  
35 a hole transport layer, another of the layers is a luminescent layer, and another of  
the layers is an electron transport layer.

1           75.    The electroluminescent device of claim 73, wherein the mixed layer is graded.

5           76.    A composition comprising a polarizable matrix comprising discrete molecules and a luminescent lanthanide metal ion.


          77.    The composition of claim 76, wherein the polarizable matrix is a long arm spiro compound.

10          78.    The composition of claim 76, wherein the polarizable matrix is:



22

20          79.    A composition comprising a polymer comprising the repeat unit:



30    where R is independently selected from H, D, F, Cl, Br, I alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, arylester, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy, any two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, and q is 0-6, A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-, -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, and r is 0-7, and E is selected from the group consisting of O, NH, and S, and one or more luminescent metal ions or luminescent metal ion complexes, wherein said polymer has a molecular weight of greater than about 30,000 Daltons.

1           80.     The composition of claim 79, wherein said polymer has a molecular weight greater than about 50,000 Daltons.

          81.     The composition of claim 79, wherein said polymer has a molecular weight greater than about 60,000 Daltons.

5           82.     The composition of claim 79, wherein said polymer has a molecular weight greater than about 100,000 Daltons.

          83.     The composition of claim 79, wherein said polymer has a molecular weight greater than about 150,000 Daltons.

          84.     The composition of claim 79, wherein said polymer has a molecular weight greater than about 200,000 Daltons.

15          85.     The composition of claim 79, wherein said polymer has an inherent viscosity of at least 1.8 dL/g.

          86.     The composition of claim 79, wherein said polymer has an inherent viscosity of at least 4.2 dL/g.

20          87.     The composition of claim 79, wherein o is 1, and R is selected from the group consisting of  $-(C=O)NR_1R_2$ , -benzoyl,  $-NR_1R_2$ ,  $-OR_1$ ,  $-CHR_1R_2$ , -phenyl, -naphthyl, and -2-benzoxazole, and  $R_1$  and  $R_2$  are as defined above.

          88.     The composition of claim 79, wherein the luminescent metal ion or luminescent metal in complex comprises a lanthanide metal ion.

          89.     The composition of claim 79, wherein the polymer is a copolymer.

30          90.     The composition of claim 79, wherein the polymer is a dendritic or hyperbranched polymer.

          91.     The composition of claim 79, wherein the luminescent metal ion or luminescent metal ion complex comprises cerium.

35          92.     The composition of claim 79, wherein the luminescent metal ion or luminescent metal ion complex comprises europium.

1           93. The composition of claim 79, wherein the luminescent metal ion or  
luminescent metal ion complex comprises terbium.

          94. The composition of claim 79, wherein the luminescent metal ion or  
luminescent metal ion complex is present as part of an inorganic solid.

5           95. The composition of claim 94, wherein the inorganic solid is a nanosized  
powder with physical dimensions in the 1 to 1000 nanometer range.

10          96. The composition of claim 94, wherein the inorganic solid is a  
semiconductor.

          97. The composition of claim 96, wherein the semiconductor is a II-VI  
semiconductor.

15          98. The composition of claim 79, wherein the luminescent metal ion or  
luminescent metal ion complex comprises a metal ion selected from the group  
consisting of chromium, manganese, iron, cobalt, molybdenum, ruthenium, rhodium,  
palladium, silver, tungsten, rhenium, osmium, iridium, platinum, gold, and  
uranium.

20          99. An electroluminescent device comprising the composition of claim 79.

          100. The composition of claim 95, wherein the inorganic solid is a  
semiconductor.

25          101. The composition of claim 95, wherein the semiconductor is a II-VI  
semiconductor.

          102. The composition of claim 101 having emission bands of 20 nm or less.











30          103. The composition of claim 101 having emission bands of 10 nm or less.









          104. The composition of claim 79 having emission bands of 5 nm or less.

35          105. The composition of claim 79 having emission bands of 3 nm or less.

106. The composition of claim 79, wherein the luminescent metal ion or luminescent metal ion complex comprises a polarizable ligand.

107. The composition of claim 106, wherein the polarizable ligand is selected from the group consisting of:



1213141516171819

108 The composition of claim 106, wherein the polarizable ligand is part of a polymer chain.

109. The composition of claim 118, wherein the polymer chain is a conjugated polymer chain.

110. The composition of claim 79, wherein the polymer is a crosslinked polymer.

111. The composition of claim 79, wherein the polymer is an oligomer.

112. The composition of claim 79, wherein the polymer is a branched polymer.

113 The composition of claim 79, wherein the polymer is a block copolymer.

1  
114. The composition of claim 79, wherein the polymer is a random copolymer.

5  
115. The composition of claim 79, wherein the polymer is a graft copolymer.

116. The composition of claim 79, wherein the conjugation length of the polymer is controlled with non-aromatic spacer groups.

10  
117. The composition of claim 116, wherein the spacer groups are selected from the group consisting of -O-, -S-, -NR-, -CR<sub>1</sub>R<sub>2</sub>-, (CH<sub>2</sub>)<sub>n</sub>-, -(CF<sub>2</sub>)<sub>n</sub>-, ester, and amide.

15  
118. The composition of claim 116, wherein the conjugation length is between 2 and 50 conjugated rings.

119. The composition of claim 116, wherein the conjugation length is between 3 and 10 conjugated rings.

20  
120. The composition of claim 116, wherein the conjugation length is between 3 and 6 conjugated rings.

25  
121. An electroluminescent device comprising:  
a first electrode;  
one or more charge transport layers; and  
an electroluminescent layer comprising the composition of claim 79 and a second electrode.

30  
122. The electroluminescent device of claim 121, wherein one or both of said electrodes is a transparent electrode.

123. The device of claim 121, wherein one or both of said electrodes comprises tin oxide or doped tin oxide.

35  
124. The device of claim 121, wherein one of the charge transport material is a hole transport material provided as a distinct layer.



1           125. The device of claim 121 comprising two layers; a first layer comprising  
a hole transport material and the electroluminescent layer.

          126. The device of claim 121, wherein an electron transport material is  
provided as a layer.

5           127. The device of claim 121 comprising two layers; a first layer comprising  
an electron transport material and the electroluminescent layer additionally  
comprising a hole transport material.

10          128. The device of claim 121 comprising three layers; the  
electroluminescent layer sandwiched between a layer of electron transport material  
and a layer hole transport material.

          129. The device of claim 128, wherein the layers are not distinct, but are  
15       graded.

          130. The electroluminescent device of claim 121 comprising a hole transport  
material and an electron transport material both of which are graded in the  
electroluminescent layer.

20          131. The electroluminescent device of claim 121, wherein the emission  
bands are 20 nm or less.

          132. The electroluminescent device of claim 121, wherein the emission  
25       bands are 10 nm or less.

          133. The electroluminescent device of claim 121, wherein the emission  
bands are 5 nm or less.

30          134. The electroluminescent device of claim 121, wherein the emission  
bands are 3 nm or less.

          135. The electroluminescent device of claim 121, wherein the  
electroluminescent layer comprises a nanosized powder with physical dimensions in  
35       the 1 to 1000 nanometer range.

136. The electroluminescent device of claim 121, wherein the turn-on voltage is less than 15V.

137. The electroluminescent device of claim 121, wherein the turn-on voltage is less than 10V.


138. The electroluminescent device of claim 121, wherein the turn-on voltage is less than 5V.

139. A composition comprising a polymer of the structure:


—(R—polarizable ligand —R)—(Y)—; and one or more luminescent metal ions or metal ion complexes, wherein R is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, aryloxy, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy, any two of the R groups may be bridging, and Y is a polymer repeat unit.

140. The composition of claim 139, wherein the luminescent metal ion or luminescent metal ion complex comprises a metal ion selected from the group consisting of chromium, manganese, iron, cobalt, molybdenum, ruthenium, rhodium, palladium, silver, tungsten, rhenium, osmium, iridium, platinum, gold and uranium.


141. The composition of claim 139, wherein the polarizable ligand is selected for the group consisting of:




1




2



3




4





5




1

6





5

78


10

91011

15




12131415

20

16








25






30

171819

35



142. The composition of claim 139, wherein Y is selected from the group consisting of:














where R on the Y repeat unit(s) is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, arylester, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy, any two of the Y repeat unit R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, and q is 0-6, A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-, -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, and r is 0-7, and E is selected from the group consisting of O, NH, and S.

143. A composition comprising a polymer comprising repeat units selected from the group consisting of:





35 where R is independently selected from H, D, F, Cl, Br, I, alkoxy, aryloxy, alkyl, aryl, alkyl ketone, aryl ketone, alkylester, aryloxy, amide, carboxylic acid, fluoroalkyl, fluoroaryl, polyalkylene oxy, any two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, and q is 0-6, A and B are independently selected from the group consisting of -O-, -S-, -NR<sub>1</sub>-, and -CR<sub>1</sub>R<sub>2</sub>-, -CR<sub>1</sub>R<sub>2</sub>CR<sub>3</sub>R<sub>4</sub>-, -N=CR<sub>1</sub>-,

1 -CR<sub>1</sub>=CR<sub>2</sub>-, -N=N-, and -(CO)- where R<sub>1</sub>-R<sub>4</sub> are H, D, F, alkyl, aryl, alkyleneoxy, polyalkyleneoxy, alkoxy, aryloxy, fluoroalkyl, and fluoroaryl, two of the R groups may be bridging, m is 0-2, n is 0-3, o is 0-4, p is 0-5, q is 0-6, and r is 0-7, and E is selected from the group consisting of O, NH, and S; and

5 one or more luminescent metal ions or luminescent metal ion complexes.

144. The composition of claim 143, wherein said polymer has a molecular weight greater than about 50,000 Daltons.

10 145. The composition of claim 143, wherein said polymer has a molecular weight greater than about 60,000 Daltons.

146. The composition of claim 143, wherein said polymer has a molecular weight greater than about 100,000 Daltons.

15 147. The composition of claim 143, wherein said polymer has a molecular weight greater than about 150,000 Daltons.


20 148. The composition of claim 143, wherein said polymer has a molecular weight greater than about 200,000 Daltons.

149. The composition of claim 143, wherein said polymer has an inherent viscosity of at least 1.8 dL/g.

25 150. The composition of claim 143, wherein said polymer has an inherent viscosity of at least 4.2 dL/g.

30

35



*FIG. 1*





*FIG. 2*

FIG. 3






FIG. 4




FIG. 5

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US01/18867

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : COSK 3/05, 3/10; H01J 1/62; H01L 33/00

US CL : 257/103; 313/503, 506; 524/403, 440

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 257/103; 313/503, 506; 524/403, 440

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WEST

search terms: oled, organic light emitting diode, electroluminescent, lanthanide, europium, terbium

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,756,224 A (BORNER et al) 26 May 1998, abstract, claims, column 5, lines 20-25; column 6, lines 10-11.	1-150
Y	US 5,834,894 A (SHIRASAKI et al) 10 November 1998, abstract and claims.	1-150



Further documents are listed in the continuation of Box C.



See patent family annex.

* Special categories of cited documents:	T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	X	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	Y	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	X	document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means		
"P" document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

18 SEPTEMBER 2001

Date of mailing of the international search report

30 OCT 2001

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

EDWARD CAIN

Telephone No. (703) 305-0661